



CDW Consultants, Inc.

MicroVision Labs Coal Ash Report, Job Number: 13409 CDW Consultants, Inc. Project Number: 1830 CDW Consultants, Inc. Project Name: Beaver St

Scope of Work:

This report covers the methods and findings of the Coal/Coal Ash analysis that MicroVision Laboratories, Inc. conducted on Three (3) soil samples submitted for testing from the Beaver St project, number 1830. The purpose of this analysis was to detect and document any coal, coal ash, wood ash or asphalt that may be present in the submitted soil samples by use of a combination of microscopy techniques including SEM/EDS, PLM, and macroscopic inspection.

Methods:

MicroVision Labs is accredited to the ISO/IEC 17025:2017 standard. This analysis follows our in house SOP #MVL05 (Microscopic Analysis for Coal, Coal Ash and Wood Ash). This method is listed on our certificate of accreditation and has been validated.

Findings:


The following pages display the data for each particle type detected in the samples for this project. Each page contains a PLM image, SEM image, and EDS spectrum for the particle types detected for these samples as well as particle type descriptions and observations.

Page 2 12/31/2019

Sample: HB-5 (0-1')


Number of Suspect Particle Types: Three (3)

Coal: This particle type consisted of eleven (11) shiny, black grains approximately 1-3mm in diameter. The PLM examination indicated this particle type to be consistent with coal. The PLM and SEM images of this particle type show the angular edges and typical conchoidal fractures found in coal.



PLM Image SEM Image


The EDS spectrum, shown below, confirms that this particle type is coal. The analysis for this particle shows concentrations of carbon, oxygen and sulfur.



ISO/IEC 17025:2017 Accredited

Page 3 12/31/2019


Coal Ash: This particle type consisted of four (4) dark, porous grains approximately 1-3mm in diameter. The PLM examination indicated this particle type to be consistent with coal ash. The PLM and SEM images show the spherical gas voids that formed during combustion.



PLM Image

SEM Image


The EDS spectrum, shown below, indicates this particle type is coal ash. The analysis for this particle shows concentrations of carbon, oxygen, sodium, magnesium, aluminum, silicon, potassium, titanium and iron.



ISO/IEC 17025:2017 Accredited


Page 4 12/31/2019

Wood Ash: This particle type consisted of two (2) friable, black grains approximately 2mm in length. The PLM examination indicated this particle type to be consistent with wood ash. The PLM and SEM photos show the cellular structure typical of wood still present in these grains.



PLM Image SEM Image

The EDS spectrum, shown below, indicates this particle type is wood ash. The analysis for this particle shows concentrations of carbon, oxygen, magnesium, aluminum, silicon, phosphorus, sulfur, chlorine, potassium, calcium and iron.




ISO/IEC 17025:2017 Accredited

Page 5 12/31/2019

Sample: GP4-1 (3-5)

No coal, coal ash, wood ash, or asphalt particles were detected in this sample.


Minerals: This particle type consisted of over one hundred (100+) shiny, dark grains 1-10mm in diameter. The PLM examination indicated this particle type to be consistent with mineral matter. The PLM and SEM images of this particle type are shown below.



PLM Image

SEM Image

The EDS spectrum results, shown below, indicate this particle type is minerals. The analysis for this particle shows concentrations of carbon, oxygen, sodium, magnesium, aluminum, silicon, phosphorus, sulfur, chlorine, potassium, calcium, titanium and iron.




ISO/IEC 17025:2017 Accredited

Page 6 12/31/2019


Sample: GP3-4 (3-5')

Number of Suspect Particle Types: Two (2)

Coal: This particle type consisted of six (6) shiny, black grains approximately 1-3mm in diameter. The PLM examination indicated this particle type to be consistent with coal. The PLM and SEM images of this particle type show the angular edges and typical conchoidal fractures found in coal.




The EDS spectrum, shown below, confirms that this particle type is coal. The analysis for this particle shows concentrations of carbon, oxygen and sulfur.



ISO/IEC 17025:2017 Accredited


Page 7 12/31/2019

Coal Ash: This particle type consisted of two (2) dark, porous grains approximately 2-4mm in diameter. The PLM examination indicated this particle type to be consistent with coal ash. The PLM and SEM images show the spherical gas voids that formed during combustion.



PLM Image SEM Image

The EDS spectrum, shown below, indicates this particle type is coal ash. The analysis for this particle shows concentrations of carbon, oxygen, sodium, magnesium, aluminum, silicon, potassium, calcium, titanium and iron.



ISO/IEC 17025:2017 Accredited

Results Summary Table:

Sample Name	Material Detected
HB-5 (0-1')	Coal (light), Coal Ash (trace), Wood Ash (trace)
GP4-1 (3-5)	Minerals (heavy)
GP3-4 (3-5')	Coal (light), Coal Ash (trace)

The concentrations of the particle types detected in these samples are listed in parenthesis in the table above and are based on the number of particles found and the relative difficulty in finding them. The concentration information is listed for informational purposes only and has no bearing on exemption status.

Please let us know if you have any questions about this analysis or if there is anything else we can do for you.

Sincerely,

Alexander Cloonan Analytical Microscopist

Reviewed by: AAC

Phon	Analytical Report Requested: YES	1	151	17/2/21 Of Call	Relinquished By: Date/Time	12)	11)	10)	9)	8)	7)	6)	5)	4)	3) 603-4(3-5) 12/1-/17	2) 6p4-1(3-5) nliwing	1) HB- 5 (0-1') "119/17	Sample ID	d		CASCHATORIES INC					ر .	
MicroVision Laboratories, Inc. 187 Billerica Road, Cheimsford, MA 01824 Phone 978-250-9909 Fax 978-250-9901 Toll Free 1-877-250-9909 microvisionlabs.com	NO	If Yes, please list:	 	E	Received By;						-				pms	S AMS	35~3	Sampler Initials	's	Email: ロシュコション	Fax	Phone: 508-305-2657	マカ	Billing A	Client: C		0
				EX	ad By; Date/Time	S. D.									X	×	×	Coal Ash Test		1507		-305	MATICIS MA	ddress:	D ~ C	Cli	hair
			(E														Lead Paint		154,5		308	200	6 14.	Client: CDW Consulants Int	Client Information	Chain Of Custody
			-						-									SEM/EDS	1	، و دعہ		-260		Billing Address: 6 HUZEN DZ,			
					me.													PLM/Light Microscopy	1 1	1 1		7			7-1		ody
			•															Soot ID	20	Censul for 15, com	PO#:	-	-17			3	<u> </u>
																		Dust ID	queste			roject	roject	roject	roject		
					um An													Unknow Mat'l ID	Requested Analyses			Manage	Project Number:	ocation	Project Name:		מסיים בי
					ound T													FTIR	888			. A. S	1830	Project Location: 360-cn-1	BEAVE ST	Proje	MicroVision Labs Job#: 5U
					ime an													Polished Cross Section				Project Manager: A・Sぃュ しゅいうつ	o	~en >1		Project Information	
					Turn Around Time and Notes:													Particle Size Analysis					-	Į	٦	nation	7
																		Wildfire						MARINA			
																		Other						3			

. ·